



中国认可
国际互认
检测
TESTING
CNAS L4350



检验检测报告

Test Report

No: MC226-230739

样品名称	Unisce 耐蚀理化板
Name of Sample	UNISCE CHEMICAL RESISTANT LAMINATE
委托单位	江苏佳饰家新材料集团股份有限公司
Applicant	JIANGSU JIASHIJIA NEW MATERIAL GROUP CO.,LTD.
生产单位	江苏佳饰家新材料集团股份有限公司
Producer	JIANGSU JIASHIJIA NEW MATERIAL GROUP CO.,LTD.
检验类别	普通送样
Category of Test	Common Sample

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 1 页

Report No. MC226-230739

Page 1 of 12

样品名称 Name of Sample	Unisce 耐蚀理化板 UNISCE CHEMICAL RESISTANT LAMINATE		检验类别 Category of Test	普通送样 Common Sample
型号规格和/或等级 Specification/Class	----		商标 Trade Mark	----
委托单位名称 Applicant	江苏佳饰家新材料集团股份有限公司 JIANGSU JIASHIJIA NEW MATERIAL GROUP CO.,LTD.			
生产单位名称 Producer	江苏佳饰家新材料集团股份有限公司 JIANGSU JIASHIJIA NEW MATERIAL GROUP CO.,LTD.			
委托单编号 Contract No.	MC22-230859	样品编号 Sample No.	MC22-230859-01	
委托日期 Date of Applicant	2023 年 09 月 22 日 22/09/2023	送样日期 Date in	2023 年 09 月 22 日 22/09/2023	
生产日期 Date of Production	----	代表批数量 Representative of batch	-----	
批号或编号 Batch No./Serial No.	-----	样品数量 Sample Quantity	500mm×500mm, 5 块 Pieces	
样品状态说明 Sample description	外观无异常 Appearance Normal			
综合判定原则 Judgment Rules	----			
检验日期 Test Date	2023 年 10 月 19 日~2023 年 10 月 20 日 19/10/2023~20/10/2023			
检验结论 Conclusions	该样品本次检验结果见检验结果汇总页。 The results of this sample are shown in the summary page of the inspection results. 检验机构（盖章） Organization (stamp) 签发日期：2023 年 10 月 25 日 Issuing date:25/10/2023			
单位地址 Address	江苏省常州市武进区横林镇卫星村南孟路 26 号 No.26 Nanmeng Road,Weixing Village,Henglin Town,Wujin District,Changzhou City,Jiangsu Province			
备注 Remarks	1、委托信息由委托方提供，本次检测仅对来样负责。 Information provided by the commission, the tests are only responsible for the sample received. 2、未经本检验机构同意，不得部分复制本报告。 Without the permission of the inspection institution, may some copy report. 3、以上检验结果受检单位如有异议，请在报告收到之日起十五日内提出。 If the units being inspected has any discrepancy about the above test, please propose after receiving the report within 15 days. 4、检验地点：申富路 568 号。 Test place: No. 568,Shen Fu Road			

批准: 张永军
Approved by审核: 杨旭
Checked by编制: 甘春辉
Prepared by

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 2 页

Report No. MC226-230739

Page 2 of 12

检验结果汇总 Test Result Collection							
序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
1	表面耐污染, 级 Resistance to staining ,grade	无水甲醇 CH ₃ OH	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
2		无水乙醇 C ₂ H ₅ OH	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
3		重铬酸钾 K ₂ Cr ₂ O ₇	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
4		乙酸乙酯 C ₄ H ₈ O ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
5		乙酸丁酯 CH ₃ COO(CH ₂) ₃ CH ₃	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
6		邻苯二甲酸二甲酯 C ₁₀ H ₁₀ O ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
7		邻苯二甲酸二乙酯 C ₁₂ H ₁₄ O ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
8		邻苯二甲酸二丁酯 C ₁₆ H ₂₂ O ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
9		乙酸戊酯 C ₇ H ₁₄ O ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
10		乙二酸二乙酯 (草酸二乙酯) C ₆ H ₁₀ O ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 3 页

Report No. MC226-230739

Page 3 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
11	表面耐污染, 级 Resistance to staining ,grade	乙酰丙酮 $C_5H_8O_2$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
12		二甲苯 C_8H_{10}	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
13		甲苯 C_7H_8	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
14		苯 C_6H_6	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
15		乙二醇 $(CH_2OH)_2$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
16		三乙醇胺 $C_6H_{15}NO_3$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
17		N,N-二甲基甲酰胺 C_3H_7NO	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
18		N,N-二甲基乙酰胺 C_4H_9NO	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
19		异丙醇 C_3H_8O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
20		1-溴丙烷 C_3H_7Br	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 4 页

Report No. MC226-230739

Page 4 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
21	表面耐污染, 级 Resistance to staining ,grade	正丁醇 (1-丁醇) $C_4H_{10}O$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
22		2-甲基-1-丙醇 $C_4H_{10}O$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
23		水合肼 $N_2H_4 \cdot H_2O$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
24		正己烷 C_6H_{14}	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
25		乙醚 $C_4H_{10}O$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
26		二氯甲烷 CH_2Cl_2	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
27		石油醚 Petroleum ether	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
28		四氯化碳 CCl_4	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
29		甲醛 CH_2O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
30		液体石蜡 mineral oil	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 5 页

Report No. MC226-230739

Page 5 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
31	表面耐污染, 级 Resistance to staining ,grade	环己胺 C ₆ H ₁₃ N	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
32		苯胺 C ₆ H ₇ N	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
33		对甲苯酚 C ₇ H ₈ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
34		二丙酮醇 C ₆ H ₁₂ O ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
35		萘 C ₁₀ H ₈	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
36		四氯化钛 TiCl ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
37		环己酮 C ₆ H ₁₀ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
38		正丙醇 CH ₃ CH ₂ CH ₂ OH	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
39		糠醛 C ₅ H ₄ O ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
40		四氯乙烯 C ₂ Cl ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 6 页

Report No. MC226-230739

Page 6 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
41	表面耐污染, 级 Resistance to staining ,grade	三氯乙烯 C ₂ HCl ₃	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
42		三乙酸甘油酯 C ₉ H ₁₄ O ₆	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
43		二乙胺 C ₄ H ₁₁ N	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
44		糠醇 C ₅ H ₆ O ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
45		甲酚 C ₇ H ₈ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
46		硝基苯 C ₆ H ₅ NO ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
47		三氯化钛 TiCl ₃	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
48		对二甲氨基苯 甲醛 C ₉ H ₁₁ NO	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
49		苯酚 C ₆ H ₆ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
50		乙硫醇 C ₂ H ₆ S	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 7 页

Report No. MC226-230739

Page 7 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
51	表面耐污染, 级 Resistance to staining ,grade	1, 2-二氯乙烯 $C_2H_2Cl_2$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
52		溴甲烷 CH_3Br	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
53		邻苯二甲酸酐 $C_8H_4O_3$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
54		邻苯二甲酸二异壬酯 $C_{26}H_{42}O_4$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
55		乙腈 CH_3CN	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
56		四氢呋喃 C_4H_8O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
57		苯甲酸苄酯 $C_{14}H_{12}O_2$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
58		冰醋酸 CH_3COOH	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
59		二硫化碳 CS_2	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
60		甲酸 $HCOOH$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 8 页

Report No. MC226-230739

Page 8 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
61	表面耐污染, 级 Resistance to staining ,grade	乳酸 $C_3H_6O_3$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
62		三氯甲烷 $CHCl_3$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
63		1, 1, 1-三氯乙烷 $C_2H_3Cl_3$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
64		1, 1, 2-三氯乙烷 $C_2H_3Cl_3$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
65		卡尔费休 Karl Fischer reagent	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
66		1, 2-二氯乙烷 $C_2H_4Cl_2$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
67		四氯乙烷 $C_2H_2Cl_4$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
68		1-辛醇 $C_8H_{18}O$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
69		苯醚 $C_{12}H_{10}O$	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
70		苯乙烯 C_8H_8	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 9 页

Report No. MC226-230739

Page 9 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
71	表面耐污染, 级 Resistance to staining ,grade	乙醇胺 C ₂ H ₇ NO	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
72		甲基异丁基酮 (4-甲基-2 戊酮) C ₆ H ₁₂ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
73		2-丁酮 C ₄ H ₈ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
74		1- 甲基-2 吡咯烷酮 C ₅ H ₉ NO	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
75		2,2,-三甲基戊烷 (异辛烷) C ₈ H ₁₈	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
76		二甲亚砜 C ₂ H ₆ OS	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
77		氯化苄 C ₇ H ₇ Cl	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
78		乙酸酐 C ₄ H ₆ O ₃	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
79		吡啶 C ₅ H ₅ N	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
80		丙酮 C ₃ H ₆ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 10 页

Report No. MC226-230739

Page 10 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
81	表面耐污染, 级 Resistance to staining ,grade	乙二胺 C ₂ H ₈ N ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
82		37%盐酸 HCl	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
83		50%硝酸 HNO ₃	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
84		磷酸 H ₃ PO ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
85		98%硫酸 H ₂ SO ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
86		高氯酸 HClO ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
87		次亚磷酸 H ₃ PO ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
88		次氯酸钠 NaClO	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
89		氢溴酸 HBr	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
90		氢氟酸 HF	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 11 页

Report No. MC226-230739

Page 11 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
91	表面耐污染, 级 Resistance to staining ,grade	30%过氧化氢 H ₂ O ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
92		氨水 NH ₃ ·H ₂ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
93		氯化铁 FeCl ₃	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
94		亚甲蓝溶液 C ₁₆ H ₁₈ N ₃ ClS	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
95		硫化钠 Na ₂ S	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
96		甲酚红乙醇 C ₂₁ H ₁₈ O ₅ S	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
97		柠檬酸 C ₆ H ₈ O ₇	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
98		甲基叔丁基醚 C ₅ H ₁₂ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
99		硫酸铜 CuSO ₄	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
100		三氯甲烷 (氯仿) CHCl ₃	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

国家建筑工程材料质量检验检测中心

National Center for Quality Inspection & Test of Building Engineering Materials

检验检测报告

TEST REPORT

报告编号: MC226-230739

共 12 页 第 12 页

Report No. MC226-230739

Page 12 of 12

检验结果汇总

Test Result Collection

序号 NO.	检测项目 Test Items		标准值 Standard Value	检测结果 Test Results		检测方法 Test Method	单项判定 Conclusion
				盖玻璃盖板 cover with glass cover	未盖玻璃盖板 cover without glass cover		
101	表面耐污染, 级 Resistance to staining ,grade	10%高锰酸钾 KMnO4	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
102		6%尿素 CH ₄ N ₂ O	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
103		氯化镁 MgCl ₂	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
104		碘酒 iodophor	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
105		汞溴红 (红药水) C ₂₀ H ₁₀ Br ₂ HgNa ₂ O ₆	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
106		磷酸三丁酯 C ₁₂ H ₂₇ O ₄ P	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
107		二正丁胺 C ₈ H ₁₉ N	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
108		2-(甲氨基)乙醇 C ₃ H ₉ NO	--	5 (无明显变化) (No obvious change)	5 (无明显变化) (No obvious change)	GB/T 17657-2013	--
说明 Explanation		1、本报告内容以中文为准。 The report is committed to the Chinese version. 2、表面耐污染的结果表示为等级 5~等级 1, 等级 5 最好。 Results of the resistance to staining is expressed as grade 5 ~ grade 1, grade 5 is best. 3、根据委托方要求, 表面耐污染性能按照 GB/T17657-2013 中 4.40 的要求进行测试, 依据步骤 A 接触时间 24h。 According to the client's requirements, resistance to staining be tested in accordance with the requirements of 4.40 in GB/T17657-2013, and the contact time shall be 24 hours according to step A.					

JC/BG 6-063-2022

(本报告内容结束)

(End of report)